

AIRLITE 3

97% Polyester
3% Carbon Suffused Nylon

	Specification	Minimum	Maximum	Test MethodJ
OZ per Square Yard	3.15	2.98	3.32	ASTM D-3776-85
Wash Shrinkage Length	5.00	2.50	7.50	AATCC-135-1987
Wash Shrinkage Width	2.50	0.00	5.00	(1(160°)x10)(A111x10)
Grab Tensile Length	54.5	39.5	69.5	ASTM D-5034
Grab Tensile Width	113.0	93.0	133.0	
Surface Resistivity				GTM
Face & Back		<1.0 x 10 ⁵		Initial
Face & Back		7.0 x 10 ⁵		After 10 Washes
Flammability	Pass			16 CFR 1610
Charge Decay	Less than 0.5 seconds per 1000 volts			GTM
Washing Instructions	Machine Wash, Warm, and Tumble Dry.			